This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF THE CLAIMS:

Claim 1 (Currently Amended) A metal oxide semiconductor (MOS) device comprising:

a semi-conducting substrate having source and drain regions;

a gate dielectric of less than 100 Å thickness on said semi-conducting substrate, said gate dielectric is selected from the group consisting of SiO_2, nitrided SiO_2, Si_3N_4, HfO_2, ZrO_3, Y_2O_3, La_2O_3, silicates or nitrogen additions of HfO_2, ZrO_3, Y_2O_3 or La_2O_3, and mixtures thereof; and

a gate formed of a metal comprising Re on top of said gate dielectric, said gate comprising Re has an interface trapped charge density of about 3E 10 cm^{-2} eV^{-1} to about 4E 10 cm^{-2} eV^{-1} ~~contains no halogens therein~~.

Claim 2 (Previously Presented) A metal oxide semiconductor device according to claim 1, wherein said gate dielectric has a thickness of less than 50 Å.

Claim 3 (Cancelled)

Claim 4 (Previously Presented) A metal oxide semiconductor device according to claim 1, wherein said gate dielectric is selected from the group consisting of HfO_2, ZrO_3, Y_2O_3, La_2O_3, and mixtures thereof including silicates and nitrogen additions.

Claim 5 (Previously Presented) A metal oxide semiconductor device according to claim1, wherein said gate dielectric is SiO_2.

Claim 6 (Cancelled)

Claim 7 (Original) A metal oxide semiconductor device according to claim 1, wherein said semi-conducting substrate is p-type or n-type.

Claim 8 (Original) A metal oxide semiconductor device according to claim 1, wherein said semi-conducting substrate is formed of a material selected from the group consisting of silicon, SiGe, SOI, Ge, GaAs, and organic semiconductors.

Claim 9 (Original) A metal oxide semiconductor device according to claim 1, wherein said semi-conducting substrate is formed of silicon.

Claim 10 (Currently Amended) A field effect transistor (FET) comprising:

a semi-conducting substrate having at least one source and one drain region;

a gate dielectric layer of less than 100 Å thickness on said semi-conducting substrate, said gate dielectric layer is selected from the group consisting of SiO_2, nitrided SiO_2, Si_3N_4, HfO_2, ZrO_3, Y_2O_3, La_2O_3, silicates or nitrogen additions of HfO_2, ZrO_3, Y_2O_3 or La_2O_3, and mixtures thereof; and

a gate formed of a metal comprising Re on top of said gate dielectric layer, said gate comprising Re <u>has an interface trapped charge density of about 3E 10 cm^{-2} eV^{-1} to about 4E 10 cm^{-2} eV^{-1}</u> ~~contains no halogens therein~~.

Claim 11 (Previously Presented) A field effect transistor according to claim 10, wherein said gate dielectric layer has a thickness of less than 50 Å.

Claim 12 (Cancelled)

Claim 13 (Previously Presented) A field effect transistor according to claim 10, wherein said gate dielectric layer is selected from the group consisting of HfO_2, ZrO_3, Y_2O_3, La_2O_3, and mixtures thereof including silicates and nitrogen additions.

Claim 14 (Original) A field effect transistor according to claim 10, wherein said semi-conducting substrate is p-type or n-type.

Claim 15 (Original) A field effect transistor according to claim 10, wherein said semiconducting substrate is formed of a material selected from the group consisting of silicon, SiGe, SOI, Ge, GaAs, and organic semiconductors.

Claim 16 (Original) A field effect transistor according to claim 10, wherein said semiconducting substrate is formed of silicon.